Håvard Gautneb (Geological Survey of Norway) 10.01.2023

Commodity	Natural graphite (C)	Data source
Significance for the EU (2023)	Critical; Strategic if battery grade	
Uses of the commodity	Main uses: Electrodes, foundry industry, refractory materials, metallurgical industry. Li-ion batteries. Carbon brushes. Minor uses: Shapes, friction products, lubricants, pencils Future uses: Refractories for the steel industry remain the dominant market. Graphite is the second largest component in Li-ion batteries, this use has seen a rapid increase in recent years, a trend which is expected to continue. Li-ion batteries demand a "spherical-type" graphite that is produced by a specialised grinding of otherwise high-quality natural graphite deposits. Large-scale fuel cells. Modular nuclear reactors (PBNRs). Vanadium redox batteries.	Taylor (2006), Latunussa et al. (2020), USGS (2023)
Resources and potential in Nordic countries	Known resources: Finland 1,276,900 t, Norway 17,985,000 t, Sweden 12,440,000 t, Greenland 6,000,000 t. Finland: Several flake graphite and extensive amorphous graphite occurrences, probably contain several Mt of fine-grained graphite. Greenland: Historic mine production and known resources suggest additional major potential. Norway: About 70 registered graphite occurrences in four main graphite provinces Sweden: At least eight graphite deposits and occurrences are known.	Lauri et al (2018), Thrane & Kalvig (2018), Beowulf Mining (2019), Leading Edge (2019), Gautneb et al. (2020), Talga Resources (2022), Rosa et al. (2023)
Anthropogenic resources and potential in Nordic countries	Recycled Li-ion batteries	
Main deposit types in Nordic countries	All economic and potentially economic graphite occurrences the Nordics are of the flake graphite type. In addition, there are large occurrences of non-economic black schist hosted deposits.	Gautneb et al. (2021)
Main global deposit types	Graphite deposits world-wide are of three types, flake graphite (55 %), amorphous graphite (43 %), and vein graphite (2 %)	Gautneb et al. (2021)
Global production (2022)	1,300,000 t (mines)	USGS (2023)
Nordic production (2021)	12,000 t (refineries / smelters)	USGS (2022)
Main producing countries (2022)	China 65.4 %, Mozambique 13.1 %, Madagascar 8.5 %, Brazil 6.7 %, South Korea 1.3 %, Canada and Russia 1.2 %, Norway 0.8 %	USGS (2023)

Critical and Strategic Metals and Minerals in Nordic countries Raw Materials for the 21st Century

Technological challenges in production	Synthetic graphite is expected to become more important in the future. In Norway, synthetic graphite is planned to be produced by Vianode, a company owned by Elkem, Hydro and Altor	https://www.vianode.com
Recycling	Present: Recycling of graphite is done to a very limited degree. Certain applications can use substitutes Future: Recycling from used batteries to increase significantly.	Latunussa et al. (2020)

References

Beowulf Mining 2019. Aitolampi graphite project. Online at: https://beowulfmining.com/projects/fennoscandian-finland-graphite/aitolampi/

Gautneb, H., Rønning, J. S., Engvik, A. K., Henderson, I. H. C., Larsen, B. E., Solberg, J. K., Ofstad, F., Gellein, J., Elvebakk, H. & Davidsen, B. 2020. The Graphite Occurrences of Northern Norway, a Review of Geology, Geophysics, and Resources. Minerals 10, 626. Online: https://doi.org/10.3390/min10070626

Gautneb, H., Gloaguen, E. and Törmänen, T. 2021. DELIVERABLE D5.3 Energy critical elements and minerals in Europe; occurrence, types, characteristics, formation, and future potential for European production (Part 1 report). GeoEra, 55. https://repository.europe-geology.eu/egdidocs/frame/d53%2Bfinal%2Bsubmitted.pdf.

Latunussa, C.E.L., Georgitzikis, K., Torres de Matos, C., Grohol, M., Eynard, U., Wittmer, D., Mancini, L., Unguru, M., Pavel, C., Carrara, S., Mathieux, F., Pennington, D. & Blengini, G.A. 2020. European Commission, Study on the EU's list of Critical Raw Materials, Factsheets on Critical Raw Materials. 819 p. Online:

https://rmis.jrc.ec.europa.eu/uploads/CRM_2020_Factsheets_critical_Final.pdf; doi: 10.2873/92480

Lauri, L.S., Eilu, P., Brown, T., Gunn, G., Kalvig, P. & Sievers, H. 2018. Identification and quantification of primary CRM resources in Europe. Deliverable 3.1 of the H2020 project SCRREEN. 63 p. Online at: http://scrreen.eu/wp-content/uploads/2018/03/SCRREEN-D3.1-Identification-and-quantification-of-primary-CRM-resources-in-Europe.pdf.

Leading Edge 2021. Woxna graphite. Online: https://leadingedgematerials.com/woxna-graphite/

Rosa, D., Kalvig, P., Stendal, H. & Keiding, J.K. 2023. Review of critical raw material resource potential in Greenland. MiMa rapport 2023/1. 121 p. https://doi.org/10.22008/gpub/32049

Talga Resources 2022. 20220527VittangiResourceUpgrade ASX.pdf (talgagroup.eu-central-1.linodeobjects.com)

Thrane, K. & Kalvig, P. 2018. Graphite potential in Greenland. Reporting on the 9th Greenland mineral resource assessment workshop, November 2017. Danmarks og Grønalnds Geologiske Undersøgelse rapport 2018/53. 42 pp.

USGS 2021. Mineral commodity summaries 2021. U.S. Geological Survey. 204 p. https://doi.org/10.3133/mcs2021 USGS 2023. Mineral commodity summaries 2023. U.S. Geological Survey. 210 p. pubs.usgs.gov/periodicals/mcs2023